Note: The following language is <u>ADDED</u> to the version of the NJTA 2004 Standard Supplementary Specifications which existed prior to the issuance of this DCA.

SECTION 907 - JOINTS

907.07 STRIP SEAL EXPANSION JOINTS.

(A) METALS.

Delete the fourth paragraph and replace it with the following:

Fabricating and welding shall meet the requirements of Subsection 403.06. Groove welds shall be partial penetration butt welds extending the full height of the extrusions and across the full width of the flats of the extrusions. Welds shall be 3/8" deep and made from the back side of the extrusion.